

Technical sheet

Indiana

Corrected grain, chrome tannage, aniline through-dyeing. Leather has a wax vintage aniline finish. Please find below the technical information provided by the producer of this leather.

Origine hides			European
Average size			4,7 m2
Thickness			0.9-1.1 mm
IUF 450 / UNI EN ISO 11640			
Colour fastness to rubbing		50 cycles dry	≥3 grey scale
		20 cycles wet	≥3 grey scale
		20 cycles sweat	≥2 grey scale
IUP 20, UNI EN ISO 5402			
Dry flexing endurance		50.000 cycles	
ISO 3377-1			
Tear Strenght		≥20 N	
IUF 470, UNI EN ISO 11644			
		N/A	N/A
UNI EN ISO105-B02 (xenon test)			
Colour fastness to artificial light		≥2-3 blue scale	

All our leathers comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo (VI) and Azo dyestuffs during the tanning process. Due to the natural properties of leather colour variations between one dye lot and another may occur.

The General Conditions of Ropelli B.V. (which are registred at Chamber of Commerce NL reg. nr. 64778010) apply on all our conventions. In particular (article 7), Client is responsible for having established whether the products meet the requirements arising from the intended use by Client. The values in this technical sheet are not a warranty in legal sense.