

Technical sheet

Outback

Natural grain, chrome tannage, stone washed leather.

Fire resistance is, UNI EN 1021/1-UNI 1021/2, BS5852 source 0.1, FAR 25853 B, Bulletin 117 California test.

Origine hides	NOT European	
Average size	4,3 m2	
Thickness	0.9-1.1 mm	
IUF 450 / UNI EN ISO 11640		
Colour fastness to rubbing	700 cycles dry	Felt clean
	150 cycles wet	Felt clean
UNI EN ISO 5402		
Flexing endurance, 50.000 cycles	no damage	
ISO 3377-1		
Tear resistance	≥20 N	
IUF 470, UNI EN ISO 11644		
Adhesion finish	>5 m/cm	
UNI EN ISO105-B02 (xenon test)		
Colour fastness to artificial light	>7 blue scale	

This leather comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo (VI) and Azo dyestuffs during the tanning process. **REACH CE1907/2006** Due to the natural properties of leather colour variations between hides & one dye lot and another may occur.

The General Conditions of Ropelli B.V. (which are registred at Chamber of Commerce NL reg. nr. 64778010) apply on all our conventions. In particular (article 7), Client is responsible for having established whether the products meet the requirements arising from the intended use by Client. The values in this technical sheet are not a warranty in legal sense.