



## Technical sheet

# Bridge

Natural grain oiled aniline leather, chrome tannage.

Origin hides			European
Average size			4.75 m <sup>2</sup>
Thickness			1,6-1,8 mm
<b>IUF 450 / UNI EN ISO 11640</b>			
Colour fastness to rubbing		50 cycles dry	≥3-4
		20 cycles wet	≥3-4
<b>UNI EN ISO 5402</b>			
Flexing endurance, 50.000 cycles			N/A
<b>ISO 3377-1</b>			
Tear resistance			≥20 N
<b>IUF 470, UNI EN ISO 11644</b>			
Adhesion finish			N/A
<b>UNI EN ISO105-B02 (xenon test, according to grey scale)</b>			
Light fastness (illumination procedure 3)			≥3 grey scale

This leather comply with the strict regulations and EU Directives covering the use and presence of PCP, CFC, Chromo (VI) and Azo dyestuffs during the tanning process. **REACH CE1907/2006** Due to the natural properties of leather colour variations between hides & one dye lot and another may occur.

The General Conditions of Ropelli B.V. (which are registred at Chamber of Commerce NL reg. nr. 64778010) apply on all our conventions. In particular (article 7), Client is responsible for having established whether the products meet the requirements arising from the intended use by Client. The values in this technical sheet are not a warranty in legal sense.